



Please check with All Custom Gasket for current lead times and availability

Tel: 905-507-4580

Fax: 905-507-4589

E-mail: gasket@allcustomgasket.com

DURLON[®] 8700

Aramid/Inorganic Fiber with CR Rubber Binder
 COMPRESSED SHEET GASKET MATERIAL
 ASTM F104: F712330-A9B5E45K5L153M5

APPLICATION:

Durlon[®] 8700 is a high-performance gasket material for use in processes requiring a neoprene (CR) bonded sheet such as refrigeration services. This product has excellent resistance to ozone, oils, non-aromatic solvents, and many refrigerants.

COMPOSITION:

Durlon[®] 8700 contains high-strength aramid and inorganic fibers bonded with high-grade neoprene (CR) rubber.

ANTI-STICK PROPERTIES:

Much effort has gone into improving the anti-stick release agents of all compressed Durlon[®] products. All Durlon[®] compressed gasket materials have passed the MIL-G-24696B Navy Adhesion Test (366°F/48 hrs).

TYPICAL PROPERTIES:

Colour	Blue
Fiber System	Aramid/Inorganic
Binder	CR
Temperature Minimum	-100°F (-73°C)
Maximum	700°F (371°C)
Continuous, max	548°F (287°C)
Pressure, max, psi (bar)	1,500 (103)
Density, g/cc (lbs/ft ³)	1.7 (106)
Compressibility, % ASTM F36	8-16
Recovery, % ASTM F36	45
Creep Relaxation, % ASTM F38	20
Tensile Strength across grain ASTM F152, psi (MPa)	1,500 (10.3)
Fluid Resistance, ASTM F146 IRM 903 Oil 5 hours at 300°F (149°C)	
Thickness Increase, %	0-15
Weight Increase, %	15
ASTM Fuel B 5 hours at 70°F (21°C)	
Thickness Increase, %	0-15
Weight Increase, %	15
Nitrogen Sealability, cc/min ASTM F2378	0.05
Flexibility, ASTM F147	8x

Note: ASTM properties are based on 1/16" sheet thickness, except ASTM F38 which is based on 1/32" sheet thickness. This is a general guide only and should not be the sole means of accepting or rejecting this material. The data listed here falls within the normal range of product properties, but should not be used to establish specification limits nor used alone as the basis of design. For applications above Class 300, consult your representative.

AVAILABLE SIZES:

Nominal Thickness		Sheet Sizes	
		Inches	mm
1/64"	0.5mm	60 x 63	1524 x 1600
		60 x 126	1524 x 3200
1/32"	0.8mm	60 x 63	1524 x 1600
		60 x 126	1524 x 3200
		120 x 126	3048 x 3200
1.0mm		60 x 63	1524 x 1600
		60 x 126	1524 x 3200
		120 x 126	3048 x 3200
1/16"	1.5mm	60 x 63	1524 x 1600
		60 x 126	1524 x 3200
		120 x 126	3048 x 3200
2.0mm		60 x 63	1524 x 1600
		60 x 126	1524 x 3200
		120 x 126	3048 x 3200
3/32"	2.5mm	60 x 63	1524 x 1600
		60 x 126	1524 x 3200
		60 x 126	3048 x 3200
1/8"	3.0mm	60 x 63	1524 x 1600
		60 x 126	1524 x 3200
		120 x 126	3048 x 3200

Warning: Durlon[®] gasket materials should never be recommended when both temperature and pressure are at the maximum listed. Properties and applications in this book are typical. No application should be undertaken by anyone without independent study and evaluation for suitability. Never use more than one gasket in one flange joint and never reuse a gasket. Improper use or gasket selection could cause property damage and/or serious personal injury. Data reported in this book is a compilation of field testing, field service reports and/or in-house testing. While the utmost care has gone into publishing the information contained herein, we assume no responsibility for errors. Specifications and information contained in this book are subject to change without notice. This edition cancels and obsoletes all previous editions.

Please check with All Custom Gasket for current lead times and availability

All Custom Gasket & Materials Limited
 355 Watline Avenue
 Mississauga, Ontario, L4Z 1P3
 Tel: 905-507-4580
 Fax: 905-507-4589
 E-mail: gasket@allcustomgasket.com
www.allcustomgasket.com



Disclaimer: The above values are typical properties and are provided for information only. They should not be used to set specification requirements. It is up to the end user to determine whether the material is suitable for the intended application.